

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (original): A magnetic recording medium, comprising:

a substrate,

at least one of undercoating layer formed on the substrate, and

a magnetic recording layer which is formed on the undercoating layer and includes a magnetic crystal grains and a grain boundary field which encloses the magnetic crystal grain; wherein

the grain boundary field includes Ti oxide, and the ratio of the substance amount of the Ti oxide in the magnetic recording layer is 5 mol % or more and 15 mol % or less, and the Ti oxide comprises at least TiO and/or Ti₂O₃.

2. (original): The magnetic recording medium according to claim 1, wherein the Ti oxide comprises TiO₂, and the component ratio of the TiO₂ in the Ti oxide is 90 mol % or less.

3. (original): The magnetic recording medium according to claim 1, wherein the magnetic crystal grain comprises Pt and Cr in addition to Co as a main component; and an orientation of a magnetic easy axis of the grain is perpendicular to the substrate.

4. (original): The magnetic recording medium according to claim 1, wherein at least one layer contained in the undercoating layer comprises nonmagnetic crystal grains which contain at least one element selected from the group consisting of Ru, Rh, Pt, and Pd as a main component.
5. (original): The magnetic recording medium according to claim 1, wherein the undercoating layer comprises: nonmagnetic crystal grains, which contains at least one element selected from the group consisting of Ru, Rh, Pt, and Pd as a main component; and a grain boundary field, which encloses the nonmagnetic crystal grains and includes an oxide of at least one element selected from the group consisting of Si, Cr, and Ti.
6. (original): The magnetic recording medium according to claim 1, wherein the ratio of the substance amount of the oxide in the undercoating layer is 1 mol % or more and 15 mol % or less.
7. (original): The magnetic recording medium according to claim 1, wherein the oxide contained in the undercoating layer is Ti oxide, and the Ti oxide comprises at least one of TiO and Ti_2O_3 .
8. (original): The magnetic recording medium according to claim 1, wherein the undercoating layer comprises TiO_2 as at least one of the Ti oxide, and the ratio of the TiO_2 in the Ti oxide is 90 mol % or less.

9. (original): A manufacturing method for a magnetic recording medium, comprising the steps of:

preparing a substrate on which an undercoating layer is formed; and

vapor-depositing a material for magnetic crystal grains and a material comprising at least one of TiO and Ti_2O_3 to form a magnetic recording layer which includes magnetic crystal grains and a grain boundary field, which encloses the magnetic crystal grains.

10. (original): The manufacturing method for a magnetic recording medium according to claim 9, wherein the grain boundary field in the magnetic recording layer includes Ti oxide, and the ratio of the substance amount of the Ti oxide in the magnetic recording layer is 5 mol % or more and 15 mol % or less.

11. (original): The manufacturing method for a magnetic recording medium according to claim 9, wherein the Ti oxide in the magnetic recording layer comprises TiO_2 , and the component ratio of the TiO_2 in the Ti oxide is 90 mol % or less.

12. (original): The manufacturing method for a magnetic recording medium according to claim 9, wherein the magnetic crystal grains in the magnetic recording layer comprise Pt and Cr in addition to Co as a main component; and an orientation of a magnetic easy axis of the grain is perpendicular to the substrate.

13. (original): The manufacturing method for a magnetic recording medium according to claim 9, wherein at least one layer contained in the undercoating layer includes nonmagnetic crystal grains which contain at least one element selected from the group consisting of Ru, Rh, Pt, and Pd as a main component.

14. (currently amended): The manufacturing method for a magnetic recording medium according to ~~any one of~~ claim 9, wherein at least one layer contained in the undercoating layer comprises: nonmagnetic crystal grains, which contains at least one element selected from the group consisting of Ru, Rh, Pt, and Pd as a main component; and a grain boundary field, which encloses the nonmagnetic crystal grains and includes an oxide of at least one element selected from the group consisting of Si, Cr, and T.

15. (original): The manufacturing method of a magnetic recording medium according to claim 9, wherein the ratio of the substance amount of the oxide in the undercoating layer is 1 mol % or more and 15 mol % or less.

16. (original): The manufacturing method of a magnetic recording medium according to claim 9, wherein the oxide contained in the undercoating layer is Ti oxide, and the Ti oxide comprises at least one of TiO and Ti_2O_3 .

Preliminary Amendment
Based on PCT/JP2004/019781

17. (original): The manufacturing method of a magnetic recording medium according to claim 9, wherein the oxide contained in the undercoating layer comprises TiO_2 as at least one of the Ti oxide, and the ratio of the TiO_2 component in the Ti oxide is 90 mol % or less.

18. (original): A magnetic read and write apparatus comprising a read and write head and the magnetic recording medium according to claim 1.

19. (original): The magnetic read and write apparatus according to claim 18, wherein the read and write head is a single pole type recording head.